



STANDARD SALES SPECIFICATION
Synthos Styrenics PS
Crystal Polystyrene
SYNTHOS PS GP Microgranulate 171 M

Property	ISO-Standard	Unit	Specification
Melt volume-flow rate (MVR 200°C/5kg)	1133	cm ³ /10 min	1.8 ± 0.8
Vicat softening temperature (VST/B50/oil)	306	°C	102 ± 3

SYNTHOS PS GP Microgranulate 170 M is crystal polystyrene with excellent flow properties and a very good overall strength.

This product is produced in conformity with our ISO 9001:2000 certified quality system.

Issued: 01/02/2017